



No. 1446115.6A

(Please quote this number in all correspondence)

CLIENT:
Floorscape Ltd.
PO Box 302365
North Harbour 0751
Auckland

SAMPLE RECEIVED FROM:
Floorscape Ltd.

Date Received: 16.12.22

SAMPLE DESCRIPTION:
Flooring Planks – PERGO Glomma Pro Hybrid

Attn.: Mike Caird

Client Order No.:

Client Reference:

1 of 2

**EN 13329:2016 – LAMINATE FLOOR COVERINGS – SPECIFICATIONS, REQUIREMENTS AND TEST METHODS
ANNEX E – DETERMINATION OF ABRASION RESISTANCE AND ABRASION CLASSIFICATION**

Note: This test was sub-contracted (Test No. 22-005139).

Wheel Type: S-42
Load (grams): 500
Abrasive Paper Changed Every: 200 Cycles

Initial Wear Point (cycles)

Specimen 1	4200
2	4100
3	4300
Mean	4200
Abrasion Class	AC4

Initial wear point was determined by recognisable wear through of the print and the sub layer exposed in three quadrants.

Table E.1 – Abrasion Classes


Abrasion Class	AC1	AC2	AC3	AC4	AC5
Average IP-value from three test specimens:	≥900	≥1800	≥2500	≥4000	≥6500

Table 2 – Classification Requirements and Levels of Use

	Levels of Use					
	Domestic			Commercial		
	Moderate	General	Heavy	Moderate	General	Heavy
Abrasion Resistance	AC1	AC2	AC3	AC4	AC5	

"THIS REPORT APPLIES ONLY TO THE SAMPLES TESTED"

Samples and their identifying descriptions have been provided by the client unless otherwise stated. NZWTA Ltd makes no warranty, implied or otherwise as to the source of the tested samples. The above results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY. This document shall not be reproduced except in full.


C Judan

Key Technical Person

02/02/2023

No. 1446115.6A

(Please quote this number in all correspondence)

CLIENT:
Floorscape Ltd.
PO Box 302365
North Harbour 0751
Auckland

SAMPLE RECEIVED FROM:
Floorscape Ltd.

Date Received: 16.12.22

SAMPLE DESCRIPTION:
Flooring Planks – PERGO Glomma Pro Hybrid

Attn.: Mike Caird

Client Order No.:


Client Reference:

2 of 2



"THIS REPORT APPLIES ONLY TO THE SAMPLES TESTED"

Samples and their identifying descriptions have been provided by the client unless otherwise stated. NZWTA Ltd makes no warranty, implied or otherwise as to the source of the tested samples. The above results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY. This document shall not be reproduced except in full.


C Judan
Key Technical Person

02/02/2023