

TEST CERTIFICATE No.: INZ78544-02

Client: Floorscape Ltd
Order No.: ISO4760 certification
Sample Description: Timber Flooring
Identification: QuickStep Imperio Engineered Timber
Material Specification: Not specified
Tested in accordance with: ISO 4760:2022(E)

Scope: SGS was engaged to test the moisture spill resistance of flooring samples supplied.

Methodology: Samples were assembled by connecting the locking edge of the plank to form a "T joint" configuration, as per figure 3 of ISO 4760:2022(E). The specimens were then conditioned at 23°C and 50% R.H for 24 h prior the surface swell test. A 100mm diameter plastic ring was glued over the inverted "T joint" with suitable sealant and a 1 kg weight placed on each corner of the test area. For each specimen, four initial height measurements were taken before water exposure. One measurement at the "T joint" position and three at the "line joint" positions. After the initial measurements were taken, 100ml of water with coloured food dye was exposed to the sealed area and allowed to stand for 24 h. The water was then removed, area patted dry and the wet swell measurement carried out within 15 min after 24 h of exposure. The specimens were allowed to stand for a further 24 h and the recovery swell measurement carried out within 15 min after 48 h of exposure.

Results:	Wet Swell(mm)	Recovery Swell(mm)
Final Avg. Thickness Swell (Pos 2-4)	0.08	0.02
Final Avg. Thickness Swell (Pos 1)	0.10	0.03
Final Avg Qualitative Rating	1	1
Observations: No leaking was observed from the underside of the plank		
Disassembly observations: No leaking through the joints was observed		

Qualitative Grade: 1 = No change 2 = Slight swelling 3 = Moderate 4 = Objectionable 5 = Failed test



Fig. 1 Test setup

Acceptance Criteria: Report findings

Tested by: C.Cheng	Reviewed By: Gijs Schoutens	Authorised By: Kelvin Chin
Date: 17-May-23	18-May-23	18-May-23

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained herein reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.
WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was(were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativeness of any goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted/Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. Samples will be retained for two (2) weeks after test date before disposal at SGS New Zealand Limited's discretion. Returning of samples to be advised in writing. Storage (when agreed by SGS New Zealand Limited) or return of samples at client's expense.