TECHNICAL DATA SHEET
Clix Plus

Valid from: 05:2025
Subject to change without notification

DIMENSIONS

Length	1261mm
Width	192mm
Thickness	8mm
Number of panels per pack	9
m² per pack	2.179m²
Bevels	4 sided
Joining System	Uniclic®

FACTORY WARRANTY

	METHOD	PARAMETERS	NORM REQUIREMENTS	CLIX VALUES
Usage class	EN 13329			Class 32
Warranty	Residential use	See warranty conditions See warranty conditions See warranty conditions	See warranty conditions See warranty conditions See warranty conditions	25-year Structural warranty 25-year Wear warranty 10-year Water-damage warranty

GENERAL DATA

	METHOD	PARAMETERS	NORM REQUIREMENTS	CLIX VALUES
Wear resistance	EN 13329		>4,000 cycles	With overlay Class 32
Wear class	EN 13329		AC4	With overlay AC4
Impact resistance	EN 13329		IC2	IC2
Scratch resistance	EN 438-2:25		Charge ≥ 3N	Charge ≥ 5N
Effect of a castor chair	ISO 4918 (with underlay)	Type W (EN 12529)	25,000 cycles	No change
Thickness swelling	ISO 24336	After 24hr immersion at 20°C	≤ 18%	≤ 12%
Locking strength	ISO 24334	F10.2 long side Fmax long side Fs0.2 short side Fmax short side	≥ 1 kN/m ≥ 2 kN/m 	≥ 1 kN/m ≥ 1 kN/m ≥ 2 kN/m ≥ 2 kN/m
Effect of furniture leg	EN 424		No damage shall be visible, when tested with foot type 0	No visible Damage
Surface soundness	EN 13329	N/mm²	≥ 1.25	≥ 1.50
Static indentation	EN 433	Residual indentation	≤ 0.05mm	No visible change
Resistance to staining	EN 438	Group 1, 2 Group 3	Class 5 Class 4	Class 5 Class 5
General appearance	EN 13329	Height difference Opening between joints Cupping in the length Cupping in the width 	≤ 0.15mm ≤ 0.20mm concave ≤ 0.50% convex ≤ 1.0% concave ≤ 0.15% convex ≤ 0.20%	≤ 0.10mm ≤ 0.10mm ≤ 0.50% ≤ 1.0% ≤ 0.15% ≤ 0.20%
Dimensional variations after changes in relative humidity	EN 13329	δl δw	δl average ≤ 0.9mm δw average ≤ 0.9mm	≤ 0.9mm ≤ 0.9mm
Light fastness	EN ISO 105 B02	Blue reference	Class > 6	Class 8

OTHER TECHNICAL DATA

	METHOD	PARAMETERS	NORM REQUIREMENTS	CLIX VALUES
Burning cigarette	EN 438-2:30		Class 4	Class 5

Premium Floors Australia Pty Ltd – 3/35 – 45 Bend Road, Keysborough VIC 3175
Floorscape Ltd – Unit C, 19 Triton Drive, Rosedale Auckland 0632 New Zealand
Email: services.australia@unilin.com T +02 9982 3441
Email: Sales.Floorscape@floorscape.co.nz T +64 9 476 0428

TECHNICAL DATA SHEET
Clix Plus

Valid from: 05:2025
Subject to change without notification

ENVIRONMENT, SAFETY & HEALTH

	METHOD	PARAMETERS	NORM REQUIREMENTS	CLIX VALUES
Formaldehyde emission	EN 717-1	ppm (large chamber)	E1 < 0.1	< 0.01
Anti-static	EN 1815		≤ 2.0 kV	≤ 2.0 kV
Reaction to fire	AS/ISO 9239.1	Class		5.6kW/m^2 / Smoke 10%
Thermal resistance	EN 12996:2001	m^2K/W	With underlay	0.1 m^2K/W
Floor heating		On recommended underlay	See special installation instructions	Suitable
Slip resistance	AS 4586	Pendulum test		P2 Linen/Toasted Almond /Autumn Oak P3 All other SKU/Décor

Premium Floors Australia Pty Ltd – 3/35 – 45 Bend Road, Keysborough VIC 3175
Floorscape Ltd – Unit C, 19 Triton Drive, Rosedale Auckland 0632 New Zealand
Email: services.australia@unilin.com T +02 9982 3441
Email: Sales.Floorscape@floorscape.co.nz T +64 9 476 0428