



### General Data

Panel	2200 x 145mm (Oak) 1820mm x 134mm (Aust.)
Total Thickness	±13mm nominal
Number of lengths per pack	6
Pack contents	Includes some shorter boards
Quantity per pack	1.914m <sup>2</sup> /1.463m <sup>2</sup>
Pack weight	21.67kg / 16.01kg
Quantity per pallet	126.324m <sup>2</sup> (66 packs Oak) 102.41m <sup>2</sup> (70 packs Aust.)
Bevel	Long sides

### Panel Build Up

Surface layer thickness	PEFC controlled sources	EN 13489	± 2.5mm nominal
Core layer thickness	PEFC controlled sources	HDF Mastercore	± 9mm nominal
Backing layer	PEFC controlled sources	Spruce	2mm
Joining system	Unilic® 4 sides		

### Warranty Information

Domestic / Residential Use	25-year Residential Wear Warranty*	
Unilic® joining system	Lifetime*	
Structural warranty	Lifetime*	
Commercial warranty	On request	
Edge Protect +	Provides a warranty against moisture staining along the board's edges	15-years*
Surface & Edge Protect + (lacquered products only)	Provides a warranty against dirt trapped within the surface coating of a board	15-years*
Waterproof Surface	Provides a warranty against water damage excluding flooding or appliance failure	15-years*

\*Conditions apply - seek warranty terms and conditions for more information

### Surface Layer

Wood species	Oak / Blackbutt / Spotted Gum	
Origin	Europe / Australia	
Finishing level	Extra matt	
Finishing treatment	UV cured lacquer	7 layers of anti-scratch UV acrylic lacquer
Natural variance	As a natural product, colour, grain and level of natural features will vary from board to board and most often deviate from samples provided.	
Surface treatments	Stains, bevels and surface textures vary by product - refer to website, brochure and samples.	





### Panel Build Up

	Surface Layer (visible elements)	
	Vibrant Grade Refers to AMT3844, AMT3845, AMT3846, AMT3849, AMT3850, AMT3851	AS2796 Medium Feature Grade (Std & Better) Refers to AMT3858, AMT3859
Sound sapwood	Permitted, colour stained	Permitted
Knot size (EN1310/AS2796)	≤ 80mm	≤ 40mm
Knot frequency	Unlimited	Unlimited
Knot filling	Half or fully filled	Fully filled
Checks/Cracks	Permitted if closed crack ≤ ½ the pack length	Permitted unlimited
Bark pockets	Not permitted	Not permitted
Grain structure	Unlimited	Unlimited
Colour variation	Lively variation	Unlimited / Very lively
Medullary ray	Permitted	Permitted
<b>Core Layer and Backing Layer (non-visible elements)</b>		

All features permitted (no limitation) as to size or quantity if these do not impair the strength or quality of the parquet flooring.

Installation	Standard / Norm requirements	Quick-Step values
Floating Installation	Always install on Quick-Step Underlay in accordance with the Installation Instructions	
Direct Stick Installation	Always install using Quick-Step MS Polymer in accordance with the Quick-Step Direct Stick Installation Instructions	
Machining tolerances	Lipping between boards- difference in height at joins (mm)	≤ 0.50mm
	Difference in board width (mm) - (EN13489)	≤ 0.20
	Cupping across width of board % - (EN13489)	≤ 0.2
Dimensional stability	Cupping short side max % - (ISO 24339)	≤ 0.30
	Cupping short side min % - (ISO 24339)	≥ 0.20
	Changes 30 – 85 % RH	≥ 0.15
	Open joints short side join (mm) - (ISO 24339)	≤ 0.20
	Open joints long side join (mm) - (ISO 24339)	≤ 0.30
Underfloor heating	Blackbutt and Spotted Gum are not suitable. European Oak is suitable for floating installation over underfloor heating. Please see special installation instructions for Quick-Step floors over heated sub-floors.	





Valid from: 11:2023

Subject to change without notification

### Technical Performance

Wear resistance	DIN 68861	S33	>550 cycles
Stain resistance	EN 13442 Floors with Edge Protect+	All except blue ink	Class 5
		Blue ink	Class 3
		Floors with Surface Protect + (Lacquered only)	Class 5
CE	EN 14342:2013	Notified body	0766 EPH Dresden DOP QW 0507
Castor chairs	ISO 4918	Tested with underlay	25.000
Slip resistance	AS4586	Pendulum test	P3
Emission of formaldehyde	EN 717-1	Large Chamber	≤ E1
PCP		CEN/TR 14823:2004	≤ 5 ppm
Heat resistance	EN 12664: 2001		0,14 m <sup>2</sup> .K/W
Reaction to fire	ISO 9239.1		4.6 kW/m <sup>2</sup> / 13% smoke

### Environmental Certificates

AFFSET	A	France
PEFC	PEFC/07-32-37	
EPD	Available on request	

