

General data

Panel	2200 x 220 mm
Total thickness	14 mm
Numbers of panels per pack	4
m ² per pack	1,9360 m ²

Panel build up

Toplayer	PEFC controlled sources	EN 13489	3,2 mm
Core board	PEFC controlled sources		Spruce
Backing layer	PEFC controlled sources	Spruce or Pine	2 mm
Tongue and groove	Length		Uniclic
	Width		Uniclic Multifit

Surface layer

Wood species	Oak
Origine	Europe
Finishing	cf catalogue/website
Grading	cf catalogue/website

Installation

Installation		Norm requirements	Quick-Step values
Floating	On Quick-Step underlay	CF installation instructions	
Glued to subfloor	Quick-Step MS polymer resin	CF installation instructions	
General aspect of installed flooring	EN 13489	Lipping - difference in height (mm)	≤ 0,20
		difference in width (mm)	≤ 0,15
		cupping lengthwise %	≤ 0,1
		cupping in width %	≤ 0,2
Dimensional stability	ISO 24339	Cupping short side max %	≤ 0,30
	Changes 30 - 85 % RH	Cupping short side min %	≥ - 0,20
		Open joints short side (mm)	≤ 0,20
		Open joints long side (mm)	≤ 0,30

Warranty

Domestic use	Conditions in each pack	33 years
Uniclic connection		Lifetime
Commercial		On request

Finishing

UV Oiled finish		2 layers	
UV cured varnish	Anti-scratch top coat	5 - 7 layers	
Wear resistance	SIS 923509	Falling sand	800 - 1000
	DIN 68861	S 33	100 - 1050
Stain resistance	EN 13442	All except blue ink	class 5
		Blue ink	class 3
CE	EN 14342: 2008-09	notified body	0766 EPH Dresden
Castor chairs	Use soft castors, type W (EN 12529) and/or suitable office mat		
Slip resistance	CEN/TS 15676 : 2008		USRV 48-52
Emission of formaldehyde	EN 717-1		E1
PCP			below detection limit
Heat resistance	EN 12664: 2001		0,14 m ² .K/W
Underfloor heating	Suitable	CF special installation instructions	
Reaction to fire	EN 14501-1		Dfl-s1

Ecological certificates

U-zeichen	Z.156.606-898
AFFSET	A
PEFC	PEFC/07-32-37
EPD	On request

